

HELUZ 20 grinded



USE

Ground bricks laid on system thin-layer mortar designed for protected load-bearing and non-load-bearing brickwork

SBC

8

40

RFI 90

1,0

GENERAL INFORMATION

Manufacturing plant
Compressive strength (MPa) $A_{10,dry,unit} (W/(m.K))$ Dimensions I x w x h (mm)
Reaction to fire class
Bulk density (kg/m³)
Average weight inf. (kg)
Additional brick production (yes/no)

MASONRY PROPERTIES ON MOI	

Bricks consumption per 1 m² (pcs)
Bricks consumption per 1 m³ (pcs)
Mortar consumption (kg/m², m²/dose, kg/m²)

THERMAL PROPERTIES

$\Lambda_{design, mas}$ (W/(m.K))
U _{design, mas} (W/(m ² .K)) without plasters
U _{design, mas} (W/(m ² .K)) with plasters
U _{dry, mas} (W/(m ² .K)) with plasters
Diffusion resistance factor μ (-)
Specific heat capacity c (kJ/(kg.K))

FIRE RESISTANCE

Wall plastered on both sides
Wall utilisation degree α

STATIC SPECIFICATIONS

Surface weight of walls with plasters (kg/m²) A group of masonry elements Masonry element strength (MPa) Compressive strength of masonry f_k (MPa) Coefficient of elasticity K_E Initial shear strength of masonry f_{vk0} (MPa)

SOUNDPROOFING

Weighted sound reduction index R_w (dB) Measured/informative value Surface weight of walls with plasters (kg/m²) Bulk density of mortar min. (kg/m³) Bulk density of plaster min. (kg/m³) Plaster thickness (mm)

ΡU

8

40

EI 60

NPD

SIDI

8

40

EI 120

NPD

2,13	2,62	5,0	1,04
0,252	0,26	0,252	0,253
0,95	0,97	0,95	0,95
0.92	0.94	0.92	0.93

SB

8

40

REI 90

1,0


0,95	0,97	0,95	0,95
0,92	0,94	0,92	0,93
0,89	0,9	0,89	0,9
5/10	5/10	5/10	5/10
1,0	1,0	1,0	1,0

185	185	185	185
2	2	2	2
10	10	10	10
3,9	3	1,9	3
1000	1000	600	700
0,3	0,3	0,12	0,3


47	47	46	46
measured	measured	indicative	indicative
152	152	NPD	NPD
900	900	NPD	NPD
1400	1400	NPD	NPD
1x15	1x15	1x15	2x15

CORNER AND LINING CONNECTION







- CORNER BONDING, 2ND ROW OF BRICKWORK



- BONDING AT THE DOOR REVEAL, 1ST ROW OF BRICKWORK



- BONDING AT THE DOOR REVEAL. 2ND ROW OF BRICKWORK



General information: The masonry properties are determined by the combination of the masonry element, mortar and surface treatment. It is therefore necessary to respect the principles for designing and building structures in accordance with the HELUZ documents and general regulations and technical standards. Detailed and up-to-date information, which always takes precedence over the technical specification, is available at constructionselector.heluz.com. The technical specifications contain a summary of selected product and structure properties to provide basic information for structure design. Unless otherwise stated, the individual data is based on harmonised European standards and their localisation for the Czech Republic.

Product properties are given according to the harmonised EN 771-1:2011+A1:2015 standard. All of the declared product parameters are listed in the declaration of performance.

Masonry properties for mortar are given for the selected mortar types in the individual columns. The mortar consumption corresponds to the execution of the masonry in accordance with

the technological regulations - HELUZ Performance Manual. Indicative labour content excludes scaffolding.

Thermal properties. The values are stated in accordance with EN 1745. A design, mas and U design, mas correspond to the design values. Coating are considered with the thickness of 2 x 15 mm with

A = 0.88 W/m.K. The heat transfer resistance used for internal structures is $R_{si} = 0.13$ m².K/W. $U_{dry,mas}$ indicates the values for coated brickwork with the bricks and mortar in the dry state. Fire resistance is stated for walls with rendering on both sides. The HELUZ SBC and HELUZ SB mortar values are stated in accordance with EN 1996-1-2, Annex B or based on test results.

HELUZ SBC and HE

The HELUZ Foam (PU) and HELUZ SIDI mortars are determined based on test results. **Soundproofing:** R_w values are determined by both wall measurement in an accredited laboratory at the specified material composition of the wall and surface weight of the masonry. The indicative values correspond to a qualified estimate based on test results of a similar brick type and material composition of the structure.